



R.E.A.L. SEAL CO.
MATERIAL DATA SHEET
COMPOUND #L-90

<u>ORIGINAL PHYSICAL PROPERTIES</u>	<u>SPEC</u>	<u>L-90</u>
HARDNESS, SHORE A PTS	90 +/-5	91
ULTIMATE TENSILE STRENGTH, PSI	5500 MIN	8622
ULTIMATE ELONGATION, %	350 MIN	532
MODULUS @ 100%, PSI	-----	1041
MODULUS @ 300% PSI	-----	3432
 <u>COMPRESSION SET (ASTM D 395B)</u>		
<u>22 HRS @ 23C</u>		
% SET	35 MAX	24
 <u>COMPRESSION SET (ASTM D 395B)</u>		
<u>22 HRS @ 70C</u>		
% SET	55 MAX	44
 <u>TEAR STRENGTH (ASTM D624 DIE C)</u>		
PLI	450 MIN	605
 <u>SPECIFIC GRAVITY</u>		
	REPORT	1.20
 <u>ABRASION RESISTANCE (ASTM D 1044)</u>		
<u>Mg/1000 CYCLES</u>		
TABER H-18 WHEEL, 1000 g LOAD	REPORT	30